

BLUEPRINT

CERAMICS

TECHNICAL DATA

ARCOTTA

TEST DESCRIPTION	TEST REQUIREMENT	VALUE
Water Absorbtion	ISO 10545-3	7%
Deep Abraison Resiatance	ISO 10545-6	544 mm3
Thermal Linear Expansion	ISO 10545-8	5,8
Thermal Shock Resistance	ISO 10545-9	Resistant
Expansion to Humidity	ISO 10545-10	0,01mm/n
Chemical resistance (**)	ISO 10545-13	Resistant
Dimensions	ISO 10545-13	Compliant
Slip resistance	DIN EN 16165 - Annex B	R13
Stain Resistance	ISO 10545-14	V1