

BLUEPRINT

CERAMICS

TECHNICAL DATA

ARC

TEST DESCRIPTION	TEST REQUIREMENT	VALUE
Retangularity	BS EN ISO 10545-2	$\pm 0,5\%$ / $\pm 2,0$ mm
Curvature Flatness	BS EN ISO 10545-2	0,5/-0,3% +2,0/-1,5 mm
Thickness	BS EN ISO 10545-2	$\pm 10\%$ / $\pm 0,5$ mm
Length & Width	BS EN ISO 10545-2	$\pm 0,5 \%$ / $\pm 2,0$ mm
Retangularity	BS EN ISO 10545-2	$\pm 0,5\%$ / $\pm 2,0$ mm
Water Absorbtion	BS EN ISO 10545-3	$\leq 10\%$
Breaking Strength	BS EN ISO 10545-4	> 600 N
Modules of Rupture	BS EN ISO 10545-4	> 12 N/mm ²
Abrasion Resistance	BS EN ISO 10545-6	3
Stain Resistance	BS EN ISO 10545-11	HA/LA/A
Chemical Resistance	BS EN ISO 10545-9	5/-/5/5